PROCESS

Technologieprozesse

Material Range	Steel, Aluminum and Aluminum Alloy, Copper Alloy, Titanium
Product Size	up to 1m Die Forming Volume for open 1000 mm, 600 mm Thickness
Precision Grade	±0.01 mm Tolerance, Laser Marking
Surface Finish	Ra 0.4 mm, including Polishing, Sandblasting, Anodizing, Electroplating, Passivation, Oil Treatment, Dry Treatment, Wet Treatment, Laser Marking
Mold Service Life	over 10 mm, 200,000 Die Punches
Delivery Time	30 Days for Mold Making, 15 Days for Sample Making, 45 Days for Mass Production
Packaging	Plastic Bag, Carton, Wooden Box, Pallet, Customized Packaging
Payment Terms	30% T/T in advance, 70% T/T before shipment, L/C at sight
Trade Terms	FOB, CIF, CFR, EXW
Port	Shanghai, NINGBO, Shenzhen, Qingdao, Tianjin, Guangzhou
Remark	Mold Maintenance, Mold Repair, Customized Services, Drawing Design

EQUIPMENT

Technologische geräte



COMMUNICATION

Close Communication with customer

PACKING

packaging and shipping